

Notice of Allowability

Application No.

10/501,673

Examiner

Tima M. McGuthry-Banks

Applicant(s)

OHTSUKA ET AL.

Art Unit

1793

-- The MAILING DATE of this communication appears on the cover sheet with the correspondence address--

All claims being allowable, PROSECUTION ON THE MERITS IS (OR REMAINS) CLOSED in this application. If not included herewith (or previously mailed), a Notice of Allowance (PTOL-85) or other appropriate communication will be mailed in due course. **THIS NOTICE OF ALLOWABILITY IS NOT A GRANT OF PATENT RIGHTS.** This application is subject to withdrawal from issue at the initiative of the Office or upon petition by the applicant. See 37 CFR 1.313 and MPEP 1308.

1. ☒ This communication is responsive to 25 October 2007.
2. ☒ The allowed claim(s) is/are 2 and 3.
3. ☒ Acknowledgment is made of a claim for foreign priority under 35 U.S.C. § 119(a)-(d) or (f).
 - a) ☒ All b) ☐ Some* c) ☐ None of the:
 1. ☐ Certified copies of the priority documents have been received.
 2. ☐ Certified copies of the priority documents have been received in Application No. _____.
 3. ☒ Copies of the certified copies of the priority documents have been received in this national stage application from the International Bureau (PCT Rule 17.2(a)).

* Certified copies not received: _____.

Applicant has THREE MONTHS FROM THE "MAILING DATE" of this communication to file a reply complying with the requirements noted below. Failure to timely comply will result in ABANDONMENT of this application.

THIS THREE-MONTH PERIOD IS NOT EXTENDABLE.

4. ☐ A SUBSTITUTE OATH OR DECLARATION must be submitted. Note the attached EXAMINER'S AMENDMENT or NOTICE OF INFORMAL PATENT APPLICATION (PTO-152) which gives reason(s) why the oath or declaration is deficient.
5. ☐ CORRECTED DRAWINGS (as "replacement sheets") must be submitted.
 - (a) ☐ including changes required by the Notice of Draftsperson's Patent Drawing Review (PTO-948) attached
 - 1) ☐ hereto or 2) ☐ to Paper No./Mail Date _____.
 - (b) ☐ including changes required by the attached Examiner's Amendment / Comment or in the Office action of Paper No./Mail Date _____.

Identifying indicia such as the application number (see 37 CFR 1.84(c)) should be written on the drawings in the front (not the back) of each sheet. Replacement sheet(s) should be labeled as such in the header according to 37 CFR 1.121(d).
6. ☐ DEPOSIT OF and/or INFORMATION about the deposit of BIOLOGICAL MATERIAL must be submitted. Note the attached Examiner's comment regarding REQUIREMENT FOR THE DEPOSIT OF BIOLOGICAL MATERIAL.

Attachment(s)

- | | |
|--|--|
| 1. <input type="checkbox"/> Notice of References Cited (PTO-892) | 5. <input type="checkbox"/> Notice of Informal Patent Application |
| 2. <input type="checkbox"/> Notice of Draftsperson's Patent Drawing Review (PTO-948) | 6. <input type="checkbox"/> Interview Summary (PTO-413), Paper No./Mail Date _____. |
| 3. <input type="checkbox"/> Information Disclosure Statements (PTO/SB/08), Paper No./Mail Date _____ | 7. <input checked="" type="checkbox"/> Examiner's Amendment/Comment |
| 4. <input type="checkbox"/> Examiner's Comment Regarding Requirement for Deposit of Biological Material | 8. <input checked="" type="checkbox"/> Examiner's Statement of Reasons for Allowance |
| | 9. <input type="checkbox"/> Other _____. |

Art Unit: 1793.

EXAMINER'S AMENDMENT

An examiner's amendment to the record appears below. Should the changes and/or additions be unacceptable to applicant, an amendment may be filed as provided by 37 CFR 1.312. To ensure consideration of such an amendment, it **MUST** be submitted no later than the payment of the issue fee.

The Abstract of the instant application has been amended according to MPEP 608.01(b) on a separate page attached.

Art Unit: 1793

The following is an examiner's statement of reasons for allowance: The prior art teaches that adding Fe_2O_3 powder to a raw material improves corrosion resistance (JP '299), preventing scale formation (JP '716) or improved wear and seizure resistance and durability (JP '709). However, the prior art of record does not teach or suggest adding Fe_2O_3 to the alloy at the mechanical alloying treatment as claimed.

Any comments considered necessary by applicant must be submitted no later than the payment of the issue fee and, to avoid processing delays, should preferably accompany the issue fee. Such submissions should be clearly labeled "Comments on Statement of Reasons for Allowance."

Any inquiry concerning this communication or earlier communications from the examiner should be directed to Tima M. McGuthry-Banks whose telephone number is (571) 272-2744. The examiner can normally be reached on M-F 7:00 am - 3:30 pm.

If attempts to reach the examiner by telephone are unsuccessful, the examiner's supervisor, Roy King can be reached on (571) 272-1244. The fax phone number for the organization where this application or proceeding is assigned is 571-273-8300.

Information regarding the status of an application may be obtained from the Patent Application Information Retrieval (PAIR) system. Status information for published applications may be obtained from either Private PAIR or Public PAIR. Status information for unpublished applications is available through Private PAIR only. For more information about the PAIR system, see <http://pair-direct.uspto.gov>. Should you have questions on access to the Private PAIR system, contact the Electronic Business Center (EBC) at 866-217-9197 (toll-free). If you would


Application/Control Number: 10/501,673

Page 4

Art Unit: 1793

like assistance from a USPTO Customer Service Representative or access to the automated information system, call 800-786-9199 (IN USA OR CANADA) or 571-272-1000.

TMM


10 January 2008

ABSTRACT

A method of manufacturing an oxide dispersion strengthened ferritic steel excellent in high-temperature creep strength having a coarse grain structure. The method comprises mixing alloy powders and an Y_2O_3 powder, subjecting the mixed powder to mechanical alloying treatment, solidifying the alloyed powder by hot extrusion, and subjecting the extruded solidified material to final heat treatment involving heating to and holding at a temperature of not less than the Ac_3 transformation point and slow cooling at a rate of not more than a ferrite-forming critical rate which comprises, 0.05-0.25% C, 8.0-12.0% Cr, 0.1-4.0% W, 0.1-1.0% Ti, 0.1-0.5% Y_2O_3 by weight, with the balance being Fe. In this method, by using a TiO_2 powder as a Ti component to be mixed at the mechanical alloying treatment or by adding a Fe_2O_3 powder, the bonding of Ti with C is suppressed, and the C concentration in the matrix does not decrease.